



Recommendations	
Product Overview	
Product Code	ES7876
Industry	Inks
Application	Screen Printing
Category	Specialty Inks
Sub-Category	Metallic
Chemistry	Plastisol
Substrate(s)	Blends, Cotton
Certification(s)	ISO9001
Curing:	
Fusion Temperature	320 °F
Gel Point	160 °F
Performance:	
Viscosity	Medium
Finish(s)	Satin Finish
Coverage	High Opacity
Printability	Great
After Flash Tack	Medium
Squeegee:	
Squeegee Profile	Square
Squeegee Type	Polyurethane
Screen:	
Mesh	86
Emulsion Type	Capillary film, Direct
Storage:	
Storage Temperature	65°F - 95°F (18°C - 35°C)

Last Change: Nov 2016

NPT COPPER 876C

ES7876 NPT COPPER and other ES NPT Metallics are formulated as a press-ready plastisol for printing on 100% Cotton or poly/cotton.

Features

- Short body and very low tack for easy printing
- Non-phthalate formulation to comply with new regulations restricting phthalates
- No viscosity modifications necessary
- Can be tinted with upto 20% color booster to make subdued metallic colors
- Extreme high luster

Instructions

NPT Metallic inks requires stirring before printing. Print directly onto substrates. NPT Metallic inks are normally printed through 86 mc in (34 mc cm). Recommend a medium Durometer squeegee for maximum coverage. NPT Metallics may tarnish and dull starting with the first wash. For maximum brilliance insure a full cure of 320°F (160°C.) and wash with garment turned inside out. Your testing should include a wash test prior to running production runs with NPT Metallic Inks to make sure the results meet your specifications.

Disclaimer:

Not all Rutland products are available in every country. Please check with your local representative for availability. The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.