



GL-901 SILVER

| Recommendations | |
|-------------------------|---|
| Product Overview | |
| Product Code | GL9010 |
| Industry | Inks |
| Application | Screen Printing |
| Category | Specialty Inks |
| Chemistry | Plastisol |
| Substrate(s) | Cotton |
| Best Used By | 12 months |
| Certification(s) | ISO9001 |
| Curing: | |
| Fusion Temperature | 325 °F |
| Performance: | |
| After Flash Tack | Decreases with increased mesh |
| Squeegee: | |
| Squeegee Profile | Square |
| Squeegee Type | Polyurethane |
| Squeegee Angle | 10° - 20° |
| Storage: | |
| Storage Temperature | 65°F - 95°F (18°C - 35°C) |
| Storage Notes | Store in a cool and dry environment. Keep container tightly closed to prevent from drying and/or contamination. |

Last Change: Nov 2016

Instructions

Printing: GL Inks can be printed through 25-40 TPI (9-15 TPcm) screens. Screens stretched to a minimum of 25 newtons are recommended. Use a 60-70 durometer squeegee. For best results 2-3 passes may be needed. Stencil: Use any direct emulsion or capillary film. Modifiers: Extend with LFP-1002 base and/or P-5011 curable reducer. Cleanup: Use any of the commercially available products for the cleanup of plastisol inks. Environmentally Friendly: QCM Plastisol Ink contains no leaded pigments and, when properly disposed of, has no environmental impact. Use a screen wash for plastisols for cleanup. Scrape screens carefully and store ink for reuse. Minimize unusable scrap ink by segregating ink by color.

Statement

QCM Textile Inks does not knowingly add plasticizers containing the phthalates listed and outlined in California Bill 1108, CPSIA HR-4040 and Oeko-tex Standard 100. The plasticizers identified may include di-(2-ethylhexyl) phthalate (DEHP), dibutyl phthalate (DBP), benzyl butyl phthalate (BBP), diisononyl phthalate (DINP), diisodecyl phthalate (DIDP), di-n-octyl phthalate (DnOP), (DIBP) Di-iso-butyl, and (DMP) Dimethylphthalate, including esters of ortho-phthalic acid and are not direct ingredients in the manufacture of Non-Phthalate Inks. QCM does not test the final product for amounts of the aforementioned phthalate plasticizers and esters and encourages all users to conduct testing for their intended use.

Disclaimer:

Not all QCM products are available in every country. Please check with your local representative for availability. The data presented are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.